Description

Special PVC film with polymeric non-migrating plasticisers for glass decoration. Its medium glossy surface inhibits undesired reflection. Available in silver and gold, as well as in different structures.

Release Paper

Silicone coated PE paper on both sides, 137 g/m², with special release characteristics which provide excellent weed-stripping properties.

Adhesive

Solvent polyacrylate, permanent

Area of use

Developed for glass areas, to achieve a hoar-frost effect or an impression of etched, cut or sandblasted glass. It is specially used for the decoration of shop windows and glass doors. Suitable for use on cutting systems. Wet application is recommended.

Technical Data

Thickness* (without paper and adhesive)	80 micron
Dimensional stability (FINAT TM 14)	Adhered to glass, no measurable shrinkage in cross
	direction, in length 0,2 mm max.
Temperature resistance***	Adhered to glass, -40° C to +90° C, no variation
Resistance to cleaning agents	Adhered to glass, 8h in washalcalics (0,5% household cleaning agents) at room temperature and 65° C, no variation
Fire behavior (DIN 4102-1)	Only flame resistant (class DIN 4102-B1) on glass with a moulded density of >= 2250 kg/m³ (indoor application)
Adhesive power* (FINAT TM 1, after 24h)	18 N/25 mm glass
	16 N/25 mm acrylic glass
Tensile strength (DIN EN ISO 527)	Along: min. 19 MPa
	Across: min. 19 MPa
Elongation at break (DIN EN ISO 527)	Along: min. 130%
	Across: min. 130%
Shelf life**	2 years
Application temperature	> +8° C
Service life by specialist application	7 years
Under vertical outdoor exposure (normal climate of Central	
Europe)	
Shelf life** Application temperature Service life by specialist application Under vertical outdoor exposure (normal climate of Central	Along: min. 130% Across: min. 130% 2 years > +8° C

Note

** in original packaging, at 20° C and 50% relative humidity

Surfaces to which the material will be applied must be thoroughly cleaned and free from dust, grease or any other contamination that could affect the adhesion of the material. Freshly lacquered or painted surfaces should be allowed to dry for at least three weeks and to completely cure. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material. Furthermore, the application information published by ORAFOL must be considered. The batch traceability according to ISO 9001 is possible on the basis of the roll number.

IMPORTANT NOTICE

* average

All ORACAL® products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects. Published information concerning ORACAL® products is based upon research which the Company believes to be reliable although such information does not constitute a warranty. Because of the variety of uses of ORACAL® products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. All specifications are subject to change without prior notice. ORACAL® is a registered trademark of ORAFOL Europe GmbH.



*** normal climate of Central Europe