

Технически данни прозрачно ПВХ Кристал 0.5мм

Item	Standard	Tolerance
Thickness	0.200mm ~ 0.50mm	Average : $\pm 5\%$ Individual: $\pm 0.03\text{mm}$
Width	21" ~ 59.1"	-0 ~ +1/4"
Weight		$\pm 3\%$
Softness	22 ~ 56 PHR	

Physical properties		Softness (PHR)			Test Method
		31 ~ 40	41 ~ 50	51 ~ 56	
Tensile Strength (kg/cm^2)	MD	230 Min.	210 Min.	180 Min.	ASTM D-882 Method A
	CD	210 Min.	190 Min.	170 Min.	
Elongation (%)	MD	200 Min.	220 Min.	260 Min.	ASTM D-882 Method A
	CD	220 Min.	240 Min.	280 Min.	
Tear Strength (kg/mm)	MD	7.0 Min.	6.0 Min.	5.0 Min.	ASTM D-1004
	CD	7.0 Min.	6.0 Min.	5.0 Min.	
Shrinkage (%)	MD	-4.0Max.	-5.0Max.	-5.0Max.	ASTM D-1204
	CD	2.0Max.	2.0Max.	2.0Max.	

Технически данни прозрачно ПВХ Кристал 0.8мм

(1) Size:

Thickness	Width	Roll length	Softness
0.60 ~ 1.0mm	36"	50 ~ 80M	28 ~ 55 PHR
	48"	40 ~ 80M	28 ~ 55 PHR
	54" ~ 59.1"	30 ~ 50M	30 ~ 55 PHR

(2) Standard:

	Standard tolerance
Thickness 0.6mm ~ 1.0mm	-5% ~ +10%
Width	-0" ~ +1/4"

(3) Test certificate

Physical properties		1.0mm x 48PHR	0.8mm X 46PHR	Test Method
Tensile Strength (kg/cm^2)	MD	278.1	253.8	ASTM D-882
	CD	230	223.1	
Elongation (%)	MD	350	338	ASTM D-882
	CD	387	385	
Tear Strength (kg/mm)	MD	8.2	8.5	ASTM D-1004
	CD	8.7	8.0	