

Технически данни на винил за ТИР завеси UNITARP 9001

Параметър	Метод за изпитание	Мерна единица	Резултат
Base Fabric	DIN 60001	-	Polyester
Yarn	DIN 60001	denier	1000 / 1000
Threads	DIN 53853	fd/ Inch	31/31,Panama
Type of coating	-	-	E - PVC
Thickness	DIN 53353	m/m	0.75
Weight	DIN 53352	gr/sq.m	900
Tensile strength	DIN 53354	Kgf/5cm	360 / 340
(STRIP METHOD)			
Elongation	DIN 53354	%	28.0 / 35.0
Tear strength	DIN 53363	Kgf	55 / 50
(TRAPEZOID)			
Adhesion strength	DIN 53357	Kgf/5cm	10
(BOND)			
Heat resistance (dimension stability)	24hr at 70°C		Warp: <1.0% Weft: <1.0%
Abrasion resistance	ASTM D 3884-92 (loss weight)	gr	0.05
Test Condition : Wheel no.: H-18(taber)		cycle : 1000 cycle	
Load : 1000gr		rpm : 70rpm	
Surface Finished	Acrylic or Fluoride	- - -	Treated
Roll length	-	M	65

Remark

M2 FLAME RETARDANT ARE AVAILABLE OPTION



Member Of HANWHA GROUP

HANWHA POLYDREAMER CO.,LTD.

Ahn

Technological Engineering Group/Leader: S.H. Ahn