
LD3880 Graphic Film



■ Features



Fire Certification

Class B. BS EN 13501-1:2007

Physical Properties

Property	Specification	Test Method
Thickness (Including adhesive)	125 µm ± 10%	Micrometer
Tensile strength	≥ 1.8kg/cm	ASTM 882
Elongation	≥ 100%	ASTM 882
Peel adhesion(24hrs)	≥ 2,000g/in	180 peeling PSTC-1
Application temp.	≥ 10 °C	18 to 25 $^{\circ}\!$
Gloss: LD3880G	60 ↑	@60, in Machine Direction
LD3880M	20 ↓	(ASTM D 2457)
Dimensional Stability Max 1.2mm		Adhered to Aluminum Plate, Length Direction (100℃ Oven, 2hr, Average)
Release liner thickness	0.14mm ± 10%	Micrometer

The information provided on this sheet represents typical properties and does not constitute a specification. No liability will be accepted for errors and omissions and in no circumstances shall LG Hausys Ltd be liable for any loss or injury arising directly or as a consequence of the publication of this data sheet. All LG Hausys vinyl sold subject to our conditions of sale. LG Hausys also retains the right to change sizes and specifications of products without prior notice.



■ Recommendation



Shelf life

Shelf life is 12 months from factory shipment. Storage condition: Free from excessive moisture, temperature, direct sunlight (20 ℃ x 50% R.H)



Durability

Durability is based on unprinted film vertical exposure Please see Durability guide of LG Hausys (www.lghausys.com)



Lamination Film


LD38 Series are recommended to use with LP3812.


Durability Guide




Durability Period & Exposure Conditions

Exposure to	Durability period		Examples
	Zone 1 & 2	Zone 3	(1 year product, Zone 1&2)
Vertical	100%	50%	1 year × 100% = 1 year
Non-Vertical	60%	30%	1 year × 60% = 0.6 year
Horizontal	30%	15%	1 year × 30% = 0.3 year







Please refer to LG Hausys durability guide of zone 1,2 and 3. (Zone system chart)

www.lghausys.com

Last Revision Date: January, 2017