

# **REFLEX PLUS SILVER**

#### **SPECIFICATIONS**

Composition	्रे Average Thickness	Carrier	<b>★</b> Certifications			
PU	170 microns	Non adhesive polyester	REACH n° 1907/2006/EU EN 20471  OEKO-TEX ® CONFIDENCE IN TEXTILES  STANDARD 100  19.HIT.86736 HOHENSTEIN HTTI			

### APPLICATION INSTRUCTIONS

⊘ Applies on	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
cotton, polyester, poly/cotton blends (not suited for treated and dye sublimated textiles)	Blade	<u></u> Pressure	>> Speed	Time	Temperature	Pressure	Peel
	45°	100 gf	15 cm/sec	5+10 seconds	155°C (311°F)	Medium (2,5/ 3,5 bar)	warm

- → Mirror cut the design
- → Weed excess material
- → Place the design on the garment
- → Transfer for 5" under suggested conditions
- → Remove the carrier in warm conditions
- → Cover with baking paper
- $\rightarrow$  Press another 10" for final fixing

#### **PRODUCT HIGHLIGHTS**

- → High retroreflectivity power
- → Follows EN ISO 20471 regulation
  - $oldsymbol{\mathcal{L}}$  NOTE: We highly recommend to perform a test before launching a production

## CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Ony cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	<b>∮</b> Position
Up to 60°C, best inside-out	YES best inside-out	YES (cotton cycle)	YES	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- → Wait 24 hours after the application before the first wash
- → Respect the textile recommendations
- → Do not bleach or use aggressive chemical agents

This document can be subject to variations. Updated versions are available on www.siser.com. For further information, please contact our sales office: info@siser.it



Siser s.r.l. Viale della Tecnica, 18 36100 Vicenza - Italy Tel. +39 0444.287960 Fax +39 0444.287959 info@siser.it www.siser.com r.e.a. vi 171856 reg. imp. vi n° 14971 c.s. € 103.300 i.v. p.iva 01591490246



